

VICTREX CT™ 100 GRA



Product Description

High performance thermoplastic material, unreinforced PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection moulding and extrusion, FDA food contact compliant, colour natural.

Typical Application Areas

Applications at very low temperatures. Wear and erosion resistant and chemically resistant to aggressive environments

MATERIAL PROPERTIES				
	CONDITIONS	TEST METHOD	UNITS	TYPICAL VALUE
Mechanical Data				
Tensile Strength	Yield, 23°C	ISO 527	MPa	95
	Break, -196°C			200
Tensile Elongation	Break, 23°C	ISO 527	%	70
	Break, -196°C			8
Flexural Strength	23°C	ISO 178	MPa	150
	-196°C			435
Flexural Modulus	23°C	ISO 178	GPa	3.5
	-196°C			5.4
Compressive Strength	23°C	ISO 604	MPa	120
	-196°C		MPa	305
Thermal Data				
Melting Point		ISO 11357	°C	343
Glass Transition (Tg)	Onset	ISO 11357	°C	143
Coefficient of Thermal Expansion	Along flow below Tg	ISO 11359	ppm K ⁻¹	45
	Average below Tg			65
Thermal Conductivity	Along flow, 23°C	ISO 22007-4	W m ⁻¹ K ⁻¹	0.32
	Average, 23°C			0.29
Flow				
Melt Viscosity	400°C	ISO 11443	Pa.s	550
Miscellaneous				
Density	Crystalline	ISO 1183	g cm ⁻³	1.30
Shore D hardness	23°C	ISO 868		84

Typical Processing Conditions					
Drying Temperature / Time	150°C / 3h or 120°C / 5h (residual moisture <0.02%)				
Temperature settings	375 / 380 / 385 / 390 / 395°C (Nozzle)				
Hopper Temperature	Not greater than 100°C				
Mould Temperature	170°C – 200°C (max 250°C)				
Runner	Die / nozzle >3mm, manifold >3.5mm				
Gate	>1mm or 0.5 x part thickness				
Mould Shrinkage + spiral flow					
Spiral Flow	395°C nozzle, 180°C tool	1mm thick section	Victrex	mm	190
		3mm thick section			630
	415°C nozzle, 180°C tool	3mm thick section			700
Mould Shrinkage	395°C nozzle, 180°C tool	Along flow	ISO 294-4	%	0.9
		Across flow			1.3

Moulding Guidelines
 Best results are obtained by using slower injection speed and higher hold pressures than for 450G

Important notes:

- Processing conditions quoted in our datasheets are typical of those used in our processing laboratories
 - Data for mould shrinkage should be used for material comparison. Actual mould shrinkage values are highly dependent on part geometry, mould configuration, and processing conditions.
 - Mould shrinkage differs for along flow and across flow directions. "Along flow" direction is taken as the direction the molten material is travelling when it exits the gate and enters the mould.
 - Mould shrinkage is expressed as a percent change in dimension of a specimen in relation to mould dimensions.
- Data are generated in accordance with prevailing national, international and internal standards, and should be used for material comparison. Actual property values are highly dependent on part geometry, mould configuration and processing conditions. Properties may also differ for along flow and across flow directions.

Detailed data available on our website www.victrex.com or upon request.

World Headquarters

Victrex plc
 Hillhouse International
 Thornton Cleveleys, Lancashire
 FY5 4QD, United Kingdom
 TEL +44 (0)1253 897700
 FAX +44 (0)1253 897701
 MAIL victrexplc@victrex.com

Victrex plc and/or its group companies ("Victrex plc") believes that the information contained in this document is an accurate description of the typical characteristics and/or uses of the product or products, but it is the customer's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy, and safety for each end-use product, device or other application. Suggestions of uses should not be taken as inducements to infringe any particular patent. The information and data contained herein are based on information we believe reliable. Mention of a product in this document is not a guarantee of availability. Victrex plc reserves the right to modify products, specifications and/or packaging as part of a continuous program of product development. Victrex plc makes no warranties, express or implied, including, without limitation, a warranty of fitness for a particular purpose or of intellectual property non-infringement, including, but not limited to patent non-infringement, which are expressly disclaimed, whether express or implied, in fact or by law. Further, Victrex plc makes no warranty to your customers or agents, and has not authorized anyone to make any representation or warranty other than as provided above. Victrex plc shall in no event be liable for any general, indirect, special, consequential, punitive, incidental or similar damages, including without limitation, damages for harm to business, lost profits or lost savings, even if Victrex has been advised of the possibility of such damages regardless of the form of action. VICTREX™, APTIV™, VICOTE™, VICTREX PIPES™, VICTREX HT™, VICTREX ST™, VICTREX WG™, PEEK-ESD™ and the Triangle (Device), are trademarks of Victrex plc or its group companies