



APTIV™ FILMS 1000

General Information

Product Description

APTIV 1000 series films are the unfilled semi-crystalline films made from VICTREX™ PEEK polymer. The film provides a material solution for engineers in ultra-high performance applications.

APTIV films are a comprehensive range of versatile, high-performance films, the use of which can facilitate reduced systems costs, improved performance and enhanced design freedom.

APTIV 1000 has a unique combination of properties providing high temperature performance, light weight, mechanical strength, durability, excellent radiation, hydrolysis and chemical resistance, electrical insulation, wear and abrasion resistance, excellent barrier properties with high purity, good flammability without the use of flame retardants, low toxicity of combustion products, and low moisture absorption in a film format. Inherently halogen free and ease of processing makes APTIV films a technology enabler for our customers and end users.

Material Properties

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.30	g/cm ³	ISO 1183
Water Absorption ¹			ISO 62
Equilibrium, 23°C, 0.0500 mm, 50% RH	0.040	%	
Shrinkage ²			
MD : 200°C, 50.0 µm	< 0.50	%	
TD : 200°C, 50.0 µm	< 0.50	%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Recommended / Available	8 to 750	µm	
Tensile Modulus			ISO 527-3
MD : 23°C, 25 µm	2600	MPa	
TD : 23°C, 25 µm	2800	MPa	
MD : 23°C, 50 µm	2500	MPa	
TD : 23°C, 50 µm	2500	MPa	
MD : 23°C, 125 µm	2400	MPa	
TD : 23°C, 125 µm	2300	MPa	
MD : 23°C, 250 µm	2300	MPa	
TD : 23°C, 250 µm	2300	MPa	
Tensile Stress			ISO 527-3
MD : Break, 23°C, 25 µm	140	MPa	
TD : Break, 23°C, 25 µm	120	MPa	
MD : Break, 23°C, 50 µm	130	MPa	
TD : Break, 23°C, 50 µm	120	MPa	
MD : Break, 23°C, 125 µm	120	MPa	
TD : Break, 23°C, 125 µm	120	MPa	
MD : Break, 23°C, 250 µm	110	MPa	
TD : Break, 23°C, 250 µm	110	MPa	

APTIV™ FILMS 1000

Films	Nominal Value	Unit	Test Method
Tensile Elongation			ISO 527-3
MD : Break, 23°C, 25 µm	> 150	%	
TD : Break, 23°C, 25 µm	> 150	%	
MD : Break, 23°C, 50 µm	> 150	%	
TD : Break, 23°C, 50 µm	> 150	%	
MD : Break, 23°C, 125 µm	> 150	%	
TD : Break, 23°C, 125 µm	> 150	%	
MD : Break, 23°C, 250 µm	> 150	%	
TD : Break, 23°C, 250 µm	> 150	%	
Trouser Tear Resistance ³			ISO 6383-1
MD : 50 µm	6.00	N/mm	
TD : 50 µm	8.00	N/mm	
Puncture Resistance (23°C, 50.0 µm)	26	kJ/m ²	Internal Method
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow ⁴ (0.0500 mm)	4.7E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ⁵ (23°C, 50 µm)	4.0E+16	ohms-cm	ASTM D257
Dielectric Strength ⁶			ASTM D149
23°C, 25 µm	270	kV/mm	
23°C, 50 µm	190	kV/mm	
23°C, 125 µm	120	kV/mm	
23°C, 250 µm	70	kV/mm	
Dielectric Constant (23°C, 50 µm, 10 MHz)	3.5		ASTM D150
Dissipation Factor (23°C, 50 µm, 10 MHz)	2.0E-3		ASTM D150
Dielectric Breakdown			ASTM D149
23°C, 25.0 µm	6750	V	
23°C, 50.0 µm	9500	V	
23°C, 125.0 µm	15000	V	
23°C, 250.0 µm	17500	V	

Notes

¹ 24 hrs

² TM-VX-84

³ 23°C

⁴ below T_g

⁵ 100 V

⁶ 0.25 inch electrode

Revision Date: November 2023

This information is provided "as is". It is not intended to amount to advice. Use of the product is at the customer's/user's risk. It is the customer's/user's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy and safety for each end-use product, device or other application and compliance with applicable laws, regulations and standards. Mention of a product is no guarantee of availability. Victrex reserves the right to modify products, data sheets, specifications and packaging. **Victrex makes no warranties, express or implied (including, without limitation, any warranty of fitness for a particular purpose or of intellectual property non-infringement) and will not be liable for any loss or damage of any nature (however arising) in connection with customer's/user's use or reliance on this information, except for any liability which cannot be excluded or limited by law.** This document may be modified or retracted at any time without notice to the customer/user.

Victrex Manufacturing Limited (or another member of the Victrex group) is the owner or the licensee of all intellectual property rights in and to this document including the following trademarks, VICTREX, INVIBIO, JUVORA, APTIV, 450G, PEEK-OPTIMA, SHAPING FUTURE PERFORMANCE, LMPAEK, TRIANGLE (Device). All rights are protected by intellectual property rights including copyright under relevant national and international intellectual property laws and treaties. All rights reserved. Copyright © Victrex Manufacturing Limited 2023.