



# APTIV™ FILMS 2100

## General Information

### Product Description

APTIV 2100 series films are the mineral filled amorphous films made from VICTREX™ PEEK polymer. The film provides a material solution for engineers in ultra-high performance applications.

APTIV films are a comprehensive range of versatile, high-performance films, the use of which can facilitate reduced systems costs, improved performance and enhanced design freedom.

APTIV 2100 has a unique combination of properties providing high temperature performance, light weight, mechanical strength, durability, excellent radiation, hydrolysis and chemical resistance, electrical insulation, wear and abrasion resistance, excellent barrier properties with high purity, good flammability without the use of flame retardants, low toxicity of combustion products, and low moisture absorption in a film format. Inherently halogen free and ease of processing makes APTIV films a technology enabler for our customers and end users. APTIV 2100 series provides a higher modulus over the APTIV 2000 series amorphous films. This grade is tailored towards thermoforming of thin wall parts with higher modulus, such as speaker diaphragms.

Please note - APTIV 2100 will crystallize if taken above the T<sub>g</sub> (143°C, 289°F) in either secondary processes or end use application. The crystallization is not reversible back to the amorphous phase without re-melting the material. Consideration of the temperature range during processing and end use application needs to be included if selecting APTIV 2100.

## Material Properties

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.42	g/cm <sup>3</sup>	ISO 1183
Shrinkage <sup>1</sup>			
MD : 200°C, 50.0 µm	< 0.50	%	
TD : 200°C, 50.0 µm	< 0.50	%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Recommended / Available	100 to 125	µm	
Tensile Modulus			ISO 527-3
MD : 23°C, 100 µm	3500	MPa	
TD : 23°C, 100 µm	3000	MPa	
MD : 23°C, 125 µm	3000	MPa	
TD : 23°C, 125 µm	3000	MPa	
Tensile Stress			ISO 527-3
MD : Break, 23°C, 100 µm	100	MPa	
TD : Break, 23°C, 100 µm	90.0	MPa	
MD : Break, 23°C, 125 µm	100	MPa	
TD : Break, 23°C, 125 µm	80.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 23°C, 100 µm	> 150	%	
TD : Break, 23°C, 100 µm	> 150	%	
MD : Break, 23°C, 125 µm	> 150	%	
TD : Break, 23°C, 125 µm	> 150	%	
Thermal	Nominal Value	Unit	
Peak Crystallization Temperature (DSC)	143	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity <sup>2</sup> (23°C, 50 µm)	1.0E+16	ohms-cm	ASTM D257

# APTIV™ FILMS 2100

## Notes

<sup>1</sup> TM-VX-84

<sup>2</sup> 100 V

**Revision Date: October 2023**

This information is provided "as is". It is not intended to amount to advice. Use of the product is at the customer's/user's risk. It is the customer's/user's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy and safety for each end-use product, device or other application and compliance with applicable laws, regulations and standards. Mention of a product is no guarantee of availability. Victrex reserves the right to modify products, data sheets, specifications and packaging. **Victrex makes no warranties, express or implied (including, without limitation, any warranty of fitness for a particular purpose or of intellectual property non-infringement) and will not be liable for any loss or damage of any nature (however arising) in connection with customer's/user's use or reliance on this information, except for any liability which cannot be excluded or limited by law.** This document may be modified or retracted at any time without notice to the customer/user.

Victrex Manufacturing Limited (or another member of the Victrex group) is the owner or the licensee of all intellectual property rights in and to this document including the following trademarks, VICTREX, INVIBIO, JUVORA, APTIV, 450G, PEEK-OPTIMA, SHAPING FUTURE PERFORMANCE, LMPAEK, TRIANGLE (Device). All rights are protected by intellectual property rights including copyright under relevant national and international intellectual property laws and treaties. All rights reserved. Copyright © Victrex Manufacturing Limited 2023.