



VICTREX LMPAEK™ POLYMER 101 GRA

General Information

Product Description

High performance thermoplastic Victrex LMPAEK™ polymer, a PEEK (PolyEtherEtherKetone) based copolymer in the PAEK (PolyArylEtherKetone) semi crystalline family. The granules may be used for additive manufacturing, melt extrusion processes or process development such as injection or compression moulding. Natural/ beige in colour.

Material Properties

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ¹	1.25	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ² (23°C)	3700	MPa	ISO 527
Tensile Stress (Yield, 23°C)	91.0	MPa	ISO 527
Tensile Strain ³ (Break, 23°C)	8.2	%	ISO 527
Flexural Modulus (23°C)	3400	MPa	ISO 178
Flexural Stress			ISO 178
Yield, 23°C	152	MPa	
3.5% Strain, 23°C	110	MPa	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ⁴ (Midpoint)	153	°C	ISO 11357
Melting Temperature ⁴	305	°C	ISO 11357
Fill Analysis	Nominal Value	Unit	Test Method
Shear Viscosity (400°C)	141	Pa·s	ISO 11443

Notes

¹ Crystalline

² Youngs

³ Tensile strain results are dependent on the moulding conditions and may demonstrate variation. Different processing methods may yield to different values.

⁴ 2nd Cycle

Revision Date: October 2024

This information is provided "as is". It is not intended to amount to advice. Use of the product is at the customer's/user's risk. It is the customer's/user's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy and safety for each end-use product, device or other application and compliance with applicable laws, regulations and standards. Mention of a product is no guarantee of availability. Victrex reserves the right to modify products, data sheets, specifications and packaging. **Victrex makes no warranties, express or implied (including, without limitation, any warranty of fitness for a particular purpose or of intellectual property non-infringement) and will not be liable for any loss or damage of any nature (however arising) in connection with customer's/user's use or reliance on this information, except for any liability which cannot be excluded or limited by law.** This document may be modified or retracted at any time without notice to the customer/user.

Victrex Manufacturing Limited (or another member of the Victrex group) is the owner or the licensee of all intellectual property rights in and to this document including the following trademarks, VICTREX, 450G, VICTREX AM, VICTREX CT, VICTREX FG, VICTREX HPG, VICTREX HT, VICTREX ST, VICTREX WG, APTIV, LMPAEK, VICOTE, TRIANGLE (Device). All rights are protected by intellectual property rights including copyright under relevant national and international intellectual property laws and treaties. All rights reserved. Copyright © Victrex Manufacturing Limited 2026.