

VICTREX™ PEEK ESD101

➤ Product Description:

High performance thermoplastic material with tight electrostatic dissipative control and low outgassing. ESD performance not influenced by moulding conditions provided that recommended processing conditions are rigorously adhered to. Semi crystalline, granules for injection moulding, easy flow, colour black.

➤ Typical Application Areas:

Applications in the semi-conductor industry where ESD control is essential while maintaining other performance requirements.

➤ Material Properties

	CONDITIONS	TEST METHOD	UNITS	TYPICAL VALUE
Mechanical Data				
Tensile Strength	Break, 23°C	ISO 527	MPa	125
	Break, -55°C			145
	Break, 120°C			80
Tensile Elongation	Break, 23°C	ISO 527	%	1.6
Tensile Modulus	23°C	ISO 527	GPa	11.5
Flexural Strength	23°C	ISO 178	MPa	200
	-55°C			230
	125°C			145
	175°C			80
	275°C			45
Flexural Modulus	23°C	ISO 178	GPa	11.0
Izod Impact Strength	Notched, 23°C	ISO 180/A	kJ m ⁻²	4.0
	Unnotched, 23°C	ISO 180/U		25
Thermal Data				
Melting Point		ISO 11357	°C	343
Glass Transition (T _g)	Onset	ISO 11357	°C	143
	Midpoint			147
Coefficient of Thermal Expansion	Along flow below T _g	ISO 11359	ppm K ⁻¹	25
	Average below T _g			40
	Along flow above T _g			70
	Average above T _g			125
Heat Deflection Temperature	1.8 MPa	ISO 75-f	°C	258
Thermal Conductivity (at 23°C)	Along flow	ISO 22007-4	W m ⁻¹ K ⁻¹	0.65
	Average			0.45
Flow				
Melt Viscosity	400°C	ISO 11443	Pa.s	275
Electrical Properties				
Volume Resistivity	23°C, 100V	IEC 60093	Ω cm	10 ⁸
Surface Resistivity	23°C, 10V	EOS/ESD S11.13	Ω/sq	10 ⁷ /10 ⁸
	23°C, 100V	EOS/ESD S11.13	Ω/sq	10 ⁶ /10 ⁷

Miscellaneous					
Density	Crystalline	ISO 1183	g cm ⁻³		1.65
Shore D hardness	23°C	ISO 868			89

Typical Processing Conditions					
Drying Temperature / Time	150°C / 3h or 120°C / 5h				
Temperature settings	365 / 370 / 375 / 380 / 385°C (Nozzle)				
Hopper Temperature	Not greater than 100°C				
Mould Temperature	180-220°C (max 250°C)				
Runner	Die / nozzle >3mm, manifold >3.5mm				
Gate	>2 mm or 0.5 x part thickness				

Mould Shrinkage and Spiral Flow					
Spiral flow	385°C nozzle, 180°C tool	1mm wall thickness	Victrex	mm	140
Mould Shrinkage	385°C nozzle, 180°C tool	Along flow	ISO 294-4	%	0.4
		Across flow		%	0.5

Moulding Guidelines					
It is essential that all sections of the mould tool are at a temperature >180°C to ensure moulded part meets ESD requirement.					
The mould temperature of >180°C must be the actual surface temperature; not the set value.					
The mould temperature should be checked using a measurement probe to confirm that the recommended minimum temperature has been achieved.					
The mould heaters must be capable of reaching and holding these high temperatures. Cartridge heaters are the suggested option.					

Important notes:

- Processing conditions quoted in our datasheets are typical of those used in our processing laboratories
Data for mould shrinkage should be used for material comparison. Actual mould shrinkage values are highly dependent on part geometry, mould configuration, and processing conditions.
Mould shrinkage differs for along flow and across flow directions. "Along flow" direction is taken as the direction the molten material is travelling when it exits the gate and enters the mould.
Mould shrinkage is expressed as a percent change in dimension of a specimen in relation to mould dimensions.
- Data are generated in accordance with prevailing national, international and internal standards, and should be used for material comparison.
 Actual property values are highly dependent on part geometry, mould configuration and processing conditions. Properties may also differ for along flow and across flow directions

Detailed data available on our website www.victrex.com or upon request



World Headquarters

Victrex plc, Hillhouse International, Thornton Cleveleys, Lancashire FY5 4QD United Kingdom

Tel: + (44) 1253 897700 Fax: + (44) 1253 897701 Email: victrexplc@victrex.com

VICTREX PLC BELIEVES THAT THE INFORMATION CONTAINED IN THIS BROCHURE IS AN ACCURATE DESCRIPTION OF THE TYPICAL CHARACTERISTICS AND/OR USES OF THE PRODUCT OR PRODUCTS, BUT IT IS THE CUSTOMER'S RESPONSIBILITY TO THOROUGHLY TEST THE PRODUCT IN EACH SPECIFIC APPLICATION TO DETERMINE ITS PERFORMANCE, EFFICACY AND SAFETY FOR EACH END-USE PRODUCT, DEVICE OR OTHER APPLICATION. SUGGESTIONS OF USES SHOULD NOT BE TAKEN AS INDUCEMENTS TO INFRINGE ANY PARTICULAR PATENT. THE INFORMATION AND DATA CONTAINED HEREIN ARE BASED ON INFORMATION WE BELIEVE RELIABLE. MENTION OF A PRODUCT IN THIS DOCUMENTATION IS NOT A GUARANTEE OF AVAILABILITY. VICTREX PLC RESERVES THE RIGHT TO MODIFY PRODUCTS, SPECIFICATIONS AND/OR PACKAGING AS PART OF A CONTINUOUS PROGRAM OF PRODUCT DEVELOPMENT. VICTREX® IS A REGISTERED TRADEMARK OF VICTREX MANUFACTURING LIMITED. VICTREX PIPES™ IS A TRADEMARK OF VICTREX MANUFACTURING LIMITED. PEEK-ESD™, HT™, ST™ AND WG™ ARE TRADEMARKS OF VICTREX PLC. VICOTE® AND APTIV® ARE REGISTERED TRADEMARKS OF VICTREX PLC.

VICTREX PLC MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, A WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR OF INTELLECTUAL PROPERTY NON-INFRINGEMENT, INCLUDING, BUT NOT LIMITED TO PATENT NON-INFRINGEMENT, WHICH ARE EXPRESSLY DISCLAIMED, WHETHER EXPRESS OR IMPLIED, IN FACT OR BY LAW. FURTHER, VICTREX PLC MAKES NO WARRANTY TO YOUR CUSTOMERS OR AGENTS, AND HAS NOT AUTHORIZED ANYONE TO MAKE ANY REPRESENTATION OR WARRANTY OTHER THAN AS PROVIDED ABOVE. VICTREX PLC SHALL IN NO EVENT BE LIABLE FOR ANY GENERAL, INDIRECT, SPECIAL, CONSEQUENTIAL, PUNITIVE, INCIDENTAL OR SIMILAR DAMAGES, INCLUDING WITHOUT LIMITATION, DAMAGES FOR HARM TO BUSINESS, LOST PROFITS OR LOST SAVINGS, EVEN IF VICTREX HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES, REGARDLESS OF THE FORM OF ACTION.